

# LAB ASPEN G12

## DESCRIPTION

Consistent cross cut chips obtained through the mechanical chopping of non chemically treated Aspen logs. Sanitized treated at high temperature through a drum dryer.



## PHYSICAL PROPERTIES

Origin : France  
Raw material : non chemically treated aspen logs  
pH : 5,0 to 5,6  
Density : 0.175 to 0.190  
Moisture content : 13 % maximum  
Particule size : 90% min. between 1 and 2 mm  
Absorption : 260 %

SERLAB UK Ltd

Lincoln House - ccfgb

300 High Holborn

London WC1V 7JH

Phone : +44 (0) 207 0923436

Email : sales@serlab.co.uk

[www.serlab.co.uk](http://www.serlab.co.uk)

## PACKAGING

10 kg autoclavable polypropylene sack  
Every bag labelled with a batch number  
39 sacks per shrink wrapped pallet

GLP Certificate  
Irradiation : optional